

PARTAC PEAT CORPORATION/BEAM CLAY®

KELSEY PARK, GREAT MEADOWS, NEW JERSEY 07838
800-247-2326 • 908-637-4191 • FAX 908-637-8421
www.beamclay.com • partac@goes.com

INSTRUCTIONS FOR REPAIRING PERMANENT PITCHER'S MOUND & BATTER'S BOX PADS

CAUTION/WARNING: READ ALL INSTRUCTIONS BEFORE USE OF MATERIALS

SOME HAZARDOUS MATERIAL ENCLOSED. (SEE MATERIALS SPECIFICATIONS AND MSDS ENCLOSED WITH KIT)

IMPORTANT: DO NOT REPAIR IF RELATIVE HUMIDITY IS GREATER THAN 68%

ADDITIONAL TOOLS YOU MAY NEED TO USE TO MAKE THE REPAIR: WIRE BRUSH, STIFF BRUSH OR BROOM, LEVEL, A 4' X 3' PIECE OF PLYWOOD, AND 2 OR 3 BRICKS.

Steps to Repair:

1. You may either remove pad from ground and repair on a flat level surface, or repair in place. To level the slope end of the pitcher's pad, slide the piece of plywood under the pad and level it with the bricks. The pad needs to be level both front to back and side to side. Only the repaired area needs to be level so material will not run off the pad. Leave rubber area in place.
2. Get all dirt off the pad areas to be repaired. Make sure pad is dry. Sweep pad with broom and then scrub with wire brush. Brush clean again or vacuum.
3. Clean area with thinner. Use a rag, or brush on. Let dry (about 2-3 minutes).
4. Paint primer on all areas to be covered. Let dry 10 - 15 minutes, or until dry.
5. Put all of Part "A" in plastic container. Mix in all of Part "B". (**CAUTION:** Part "B" is the toxic material. See enclosed MSDS sheet for information about the product.) Avoid contact with skin or eyes.
6. Stir well. Wipe edges of container to get a good mix. Part "B" should disappear into Part "A", no streaks.
7. Pour into areas needing patching. Do pitcher's rubber area first, then put all of remaining mix into landing area. Spread it out with side of mixing stick. Sprinkle some granules into mix and stir in. Sprinkle remaining granules on top.
8. The mix should begin to set in about 30 minutes. Longer on cool days, shorter on warm days. Let stand overnight.

NOTE: All containers should be disposed of in accordance with applicable local, state, or federal regulations. Do not breathe in fumes.

Clean hands with solvent then wash with soap and water. Any problems, call (800) 247-2326.

PARTAC PEAT CORPORATION/BEAM CLAY®

KELSEY PARK, GREAT MEADOWS, NEW JERSEY 07838
800-247-2326 • 908-637-4191 • FAX 908-637-8421
www.beamclay.com • partac@goes.com

REPAIR KIT **FOR PERMANENT PITCHER'S MOUNDS AND BATTER'S BOXES**

1 PINT	PART "B" (E448)
1 GALLON	PART "A" (VT 360)
1 PINT	S 2169 PRIMER
1 QUART	ZYLENE THINNER
1	SIX QUART PLASTIC BUCKET
2	PAINT MIXTURE STICKS
3	RAGS
1 QUART	BAG OF GRANULES

YOUR "ONE-STOP SOURCE" FOR AMERICA'S BASEBALL SURFACES & SUPPLIES